



MANUFACTURING CORPORATION

- Plastics Machining
- Spring Energized Seals
- Rotary Lip Seals

**Material Data Sheet**

Material: Nylatron GF® 30

30% Glass Filled Polyamide

Nylatron GF® 30 material is designed for applications that require higher compressive strength and rigidity. Nylon materials are good for bearing and wear application as well as some structural applications.

| Mechanical Properties                                    | Test Method ASTM | Value                | Units                           |
|--|------------------|----------------------|---------------------------------|
| Specific Gravity, 73°F                                   | D792             | 1.29                 |                                 |
| Tensile Strength, 73°F                                   | D638             | 13,500               | psi                             |
| Tensile Modulus of Elasticity, °F                        | D638             | 675,000              | psi                             |
| Tensile Elongation ( at break), 73°F                     | D638             | 5                    | %                               |
| Flexural Strength, 73°F                                  | D790             | 21,000               | psi                             |
| Flexural Modulus of Elasticity, 73°F                     | D790             | 650,000              | psi                             |
| Shear Strength, 73°F                                     | D732             |                      | psi                             |
| Compressive Strength, 10% Deformation, 73°F              | D695             | 18,000               | psi                             |
| Compressive Modulus of Elasticity, 73°F                  | D695             | 600,000              | psi                             |
| Hardness, Rockwell, Scale as noted, 73°F                 | D785             | M75                  |                                 |
| Hardness, Durometer, Shore "D" Scale, 73°F               | D2240            |                      |                                 |
| Izod Impact (notched), 73°F                              | D256 Type A      |                      | ft-lb/in of notch               |
| Coefficient of Friction (Dry vs. Steel) Dynamic          | QTM 55007        |                      |                                 |
| Limiting PV (with 4:1 safety factor applied)             | QTM 55007        |                      | ft.lbs./in. <sup>2</sup> min    |
| Wear Factor "k" x 10 <sup>-10</sup>                      | QTM 55010        |                      | in. <sup>3</sup> -min/ft.lbs.hr |
| <b>Thermal Properties</b>                                |                  |                      |                                 |
| Coefficient of Linear Thermal Expansion (-40°F to 300°F) | E-831 (TMA)      | 2 x 10 <sup>-5</sup> | in/in./°F                       |
| Heat Deflection Temperature 264 psi                      | D648             | 400                  | °F                              |
| TG-Glass transition (amorphous)                          | D3418            | N/A                  | °F                              |
| Melting Point (Crystalline) peak                         | D3418            | 500                  | °F                              |
| Continuous Service Temperature in Air (Max.) (1)         |                  | 220                  | °F                              |
| Thermal Conductivity                                     | F433             | 1.7                  | BTU-in/hr-ft <sup>2</sup> -°F   |
| <b>Electrical Properties</b>                             |                  |                      |                                 |
| Dielectric Strength, Short Term                          | D149             | 350                  | Volts/mil                       |
| Surface Resistivity                                      | EOS/ESD S11.11   |                      | ohm/square                      |
| Dielectric Constant, 106 Hz                              | D150             |                      |                                 |
| Dissipation Factor, 106 Hz                               | D150             |                      |                                 |
| Flammability @ 3.1 mm (1/8 in.)                          | UL 94            | V-2                  |                                 |
| FDA Compliant  |                  | No                   |                                 |

237 Glider Circle, Corona, CA 92880 Phone: (951) 272-9395 Fax: (951) 272-9397

\*The values shown in these and the following charts are typical, average properties. Actual values may differ due to variations in resin formulations and processing methods. These values are obtained from sources believed to be reliable, including the resin manufactures, converters and other published sources. However, they should not be used for specification or design purposes. Above information is provided by Quadrant EPP.