



MANUFACTURING CORPORATION

- Plastics Machining
- Spring Energized Seals
- Rotary Lip Seals

### Material Data Sheet

Material: Nylatron GSM Cast | Molybdenum Disulphide (MoS<sub>2</sub>) Filled Polyamide

Nylatron® GSM Nylon contains finely divided particles of molybdenum disulphide (MoS<sub>2</sub>) to enhance its load bearing capabilities while maintaining the impact resistance inherent to nylon. It is the most commonly used grade for gears, sheaves, sprockets and custom parts. It is grey-black in color

Mechanical Properties	Test Method ASTM	Value	Units
Specific Gravity, 73°F	D792	1.16	
Tensile Strength, 73°F	D638	11,000	psi
Tensile Modulus of Elasticity, °F	D638	400,000	psi
Tensile Elongation ( at break), 73°F	D638	30	%
Flexural Strength, 73°F	D790	16,000	psi
Flexural Modulus of Elasticity, 73°F	D790	500,000	psi
Shear Strength, 73°F	D732	10,500	psi
Compressive Strength, 10% Deformation, 73°F	D695	14,000	psi
Compressive Modulus of Elasticity, 73°F	D695	400,000	psi
Hardness, Rockwell, Scale as noted, 73°F	D785	M80(R110)	
Hardness, Durometer, Shore "D" Scale, 73°F	D2240	D85	
Izod Impact (notched), 73°F	D256 Type A	0.5	ft-lb/in of notch
Coefficient of Friction (Dry vs. Steel) Dynamic	QTM 55007	0.2	
Limiting PV (with 4:1 safety factor applied)	QTM 55007	3,000	ft.lbs./in. <sup>2</sup> min
Wear Factor "k" x 10 <sup>-10</sup>	QTM 55010	90	in. <sup>3</sup> -min/ft.lbs.hr
<b>Thermal Properties</b>			
Coefficient of Linear Thermal Expansion (-40°F to 300°F)	E-831 (TMA)	5 x 10 <sup>-5</sup>	in/in./°F
Heat Deflection Temperature 264 psi	D648	200	°F
TG-Glass transition (amorphous)	D3418	N/A	°F
Melting Point (Crystalline) peak	D3418	420	°F
Continuous Service Temperature in Air (Max.) (1)		200	°F
Thermal Conductivity	F433		BTU-in/hr-ft <sup>2</sup> -°F
<b>Electrical Properties</b>			
Dielectric Strength, Short Term	D149	400	Volts/mil
Surface Resistivity	EOS/ESD S11.11	>10 <sup>13</sup>	ohm/square
Dielectric Constant, 106 Hz	D150	3.7	
Dissipation Factor, 106 Hz	D150		
Flammability @ 3.1 mm (1/8 in.)	UL 94	HB	
FDA Compliant		No	

237 Glider Circle, Corona, CA 92880 Phone: (951) 272-9395 Fax: (951) 272-9397

\*The values shown in these and the following charts are typical, average properties. Actual values may differ due to variations in resin formulations and processing methods. These values are obtained from sources believed to be reliable, including the resin manufactures, converters and other published sources. However, they should not be used for specification or design purposes. Above information is provided by Quadrant EPP.